
jaquar.com





Brass Specification in Percentage	Brass Rod as per IS:319-1989
	Cu (56.0-59.0), Pb (2.0-3.5), Fe (0.0-0.35), Total Impurity (0.0-0.7), Zn (Remainder)
	Duran Shanta na unu IS:410, 1077
	Brass Sheets as per IS:410-1977
	Cu (61.5-64.5), Pb (0.0-0.3), Fe (0.0-0.075), Total Impurity (0.0-0.6), Zn (Remainder)
	Brass Pipe as per IS:407-1996
	Cu (62.0-65.0), Pb (0.0-0.3), Fe (0.0-0.01), Total Impurity (0.0-0.6), Zn (Remainder)
	Plating: Nickel-10.0 micron Chromium-0.3 micron
Finish	Salt Spray (500 hrs + Validated)
	Adhesion (Pass)
	(Autrestoff (Pass)
Aerator Size	WRAS, ACS Approved (20X1)

DISCLAIMER: Our every effort has been made to ensure factual accuracy, the information presented subject to changes due to requirements in different sites, markets and/ or countries. 10% variation in flow rate may be possible. Jaquar reserves the right to make the necessary amendments at any time without prior notice.